

Highly durable semi gloss protective clear sealer

Description

Avista Concrete Sealer Extended Wear seals and helps protect the substrate from ingress of dirt and grime. It also helps protect the substrate from weathering.

Uses

Avista Concrete Sealer Extended Wear can be used on most exterior concrete surfaces including stamped, stencilled, resurfaced, plain and coloured concrete. It is not suitable for internal concrete floors

NOTE: Sealers should not be used on steep or smooth concrete surfaces as it may cause the surface to become slippery, particularly when wet.

Advantages

- Protection from dirt, oil and fuel
- Excellent marking resistance
- Easy to apply

Properties

| | |
|---|--|
| Solids (PBW): | 24% ± 1% |
| UV Light: | Very good resistance |
| Thinning: | Solvent |
| Recommended Film Build: | Approx. 40-80 microns dry per coat |
| Coverage Rate: | Approx. 3-6 m ² per ltr per coat |
| 50 micron dry film cured for 28 days at 25°C before testing with 1 hour soak | |
| Alkali (1% Caustic Soda): | No visual effect |
| Mineral Turpentine: | Slight softening (rearden 8 hours) |
| Methylated spirits: | Causes white discolouration (easily removed with solvent) |
| Chlorine (Sodium Hydrochloric) 5%: | No visual effect |
| Salt (Sodium Chloride): | No visual effect |
| Brake fluid: | Softening and slight dulling - immediately clean with detergent and then solvent |

Application Instructions for New Cured and Old Concrete (unsealed)

Preparation

Ensure concrete is sufficiently cured (recommended minimum 14 days).

- Concrete is to be clean and free of grease, oil, paint or any curing agent. Stiff broom and general purpose cleaner recommended.
- Pressure clean surface at minimum 2000 psi and allow to dry.
- Acid etch with hydrochloric acid. Dilute approx 20 parts water to 1 part acid (depending on porosity) to remove any loosely bound cement and laitence.
NOTE: smooth concrete will require a higher acid content. Maximum strength - 10 parts water to 1 part acid.
- Apply diluted acid to surface using a large head watering can, applying in a criss cross motion (approximately 5-10m² sections). Acid will start to fizz on the surface once it starts to react with the laitence in the concrete.
- Pressure clean immediately to clean and remove all remnants of acid (do not allow acid to dry on surface). Pressure clean at minimum 2000 psi.
- Allow surface to dry before sealing. (sealing over damp concrete will cause whitening). Refer to Dry Test.

Application Process

Do not apply to concrete if it has a patchy appearance.

Ensure primer and sealer are not applied too thickly and no pooling occurs.

Primer

- Prime coat the surface first with Avista Concrete Sealer Primer with a roller, broom or spray and leave to dry for a minimum of 2 hours.

NOTE: For new resurfaced concrete, Avista Sealer Primer is not required. Apply 2 coats of Avista Extended Wear Sealer to resurfaced area.

Sealing

- Pour Avista Extended Wear Sealer into a roller tray and roll evenly onto the surface using a good quality roller. Allow to dry a minimum of 2 hours before applying a second coat of sealer.
- To obtain a lower slip factor it is advisable to use the appropriate Slip Reducing Additive with the sealer for better grip under adverse conditions e.g. wet areas, steep slopes and pool surround areas. See Avista Slip Reducing Additive TDS for details.

Avista Concrete Sealer Extended Wear



Application Instructions for Sealed Concrete

Testing

Cross Hatch Test is required.

This simple test should be used to ascertain whether existing sealer is suitable to be resealed over.

1. Use a sharp blade to create a light "cross-hatch" incision through the sealer.
2. Place a piece of self adhesive tape (suggest clear packing tape) over the incision.
3. Press firmly for maximum adhesion and remove sharply. Repeat with fresh tape several times.

If sealer is present on the tape, it is advised sealer be completely stripped from surface. Seek professional contractors should stripping be required.

If there is no sign of sealer adhering to the tape or delaminating from the surface, this would indicate that the bond of the existing sealer is sufficient for resealing.

IMPORTANT NOTE: if current sealer shows signs of whitening or blooming, regardless of cross hatch test results, sealer may need to be stripped completely from the surface. Whitening may reoccur if new coat of sealer is applied over this problem.

Cleaning

- Concrete is to be clean and free of grease and oil. Stiff broom and general purpose cleaner recommended.
- Pressure clean at minimum 2000 psi to clean and remove all contaminants. Allow surface to dry before resealing (sealing over damp concrete will cause whitening). Refer to Dry Test.

Solvent treatment

If the existing sealer on the surface is more than 2 years old, Solvent is required to reactivate the existing sealer. This will help with the adhesion of the new sealer coat.

- Apply Avista Solvent to the area being resealed using a roller and roller tray.
- NOTE: If resealing a resurfaced area, DO NOT apply too much Solvent as it may soften the resurfacing product.
- Complete solvent treatment of entire surface.
- Allow area to dry enough to walk on before proceeding to sealing stage.

Application Process

Do not apply to concrete if it has a patchy appearance.

Ensure sealer is not applied too thick and no pooling occurs.

Primer

- Prime coat the surface first with Avista Concrete Sealer Primer with a roller, broom or spray and leave to dry for a minimum of 2 hours.

Sealing

- Pour Avista Extended Wear Sealer into a roller tray and roll evenly onto the surface using a good quality roller. Allow to dry a minimum of 2 hours before applying a second coat of sealer.
- To obtain a lower slip factor it is advisable to use the appropriate Avista Slip Reducing Additive with the sealer for better grip under adverse conditions e.g. wet areas, steep slopes and pool surround areas. See Avista Slip Reducing Additive TDS for details.

Drying time

Minimum of 2 hours between coats when applied at 25°C and above at 50% relative humidity. Recoat times will be longer in cooler weather (<25°C) or higher humidity.

Do not apply sealer at temperatures below 8°C or above 35°C.

Curing Time

After sealing it is recommended that the sealed surface be protected from:

- Rain/water/sprinkler systems for minimum 6 hours
- Foot traffic for a minimum of 24 hours
- Vehicle traffic for a minimum of 5 days in warmer weather (>25°C) and 7 days in cooler weather (<25°C).

The time depends on weather conditions and coating thickness, therefore, check suitability before allowing traffic.

Dry Test

- Place a piece of plastic over a small area, tape the edges and leave for 1 hour.
- Remove plastic, if there is no moisture on either surface, concrete is sufficiently dry for sealing.

Avista Concrete Sealer

Extended Wear

Maintenance

Remove oil, grease and other contaminants immediately with a general purpose cleaner. Note: Surface will need to be resealed at 18-24 months.

Limitations

- Do not seal in high winds or if rain is likely.
- Do not apply over painted surfaces. Paint removal required.
- Application of sealer can lower slip resistance (slip resistance additives available).
- Not for food preparation areas.
- Not a waterproofing membrane.
- Do not use Sealer at temperatures below 8°C and above 35°C

Supply

| | |
|----------------------|-------------------------------|
| 178005/FD278006-4L | AVS EXTENDED WEAR SEALER |
| 178006/FD27006-20L | AVS EXTENDED WEAR SEALER 20L |
| 178007/FD278006-200L | AVS EXTENDED WEAR SEALER 200L |

Coverage

1 x 20 litre drum covers approximately 60 to 100m² per coat depending on the porosity of the concrete.

Shelf life

24 months if kept in unopened container and stored in cool, dry conditions. After this time, product should be checked to ensure its suitability for use.

Storage Conditions

Store in cool, dry area in unopened container. Highly flammable liquid, store appropriately. Refer to SDS.

Cleaning

Clean up with solvent.

Safety

Recommended PPE:

- Organic vapour respirator mask
- Solvent resistant gloves
- Safety eye wear
- Appropriate foot wear

Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Avista website www.avista.com.au. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

AVISTA

© Avista is a registered trademark of Parchem Construction Supplies.